



Specification of Chemically Activated Carbon

Methylene blue	300 mg/gm	310 mg/gm	310 mg/gm	260 mg/gm	250 mg/gm
Ash Content	Max 8	Max 5	Max 5	Max 5	Max 5
Acid soluble Max	2.0%	1.5%	1.5%	1.5%	1.5%
Water soluble Max	1.5%	1%	1%	1%	1%
Iron Content Max	300 PPM	200 PPM	200 PPM	200 PPM	200 PPM
Moisture Max	10%	10%	10%	10%	10%
Caramel Value Min	115%	120%	120%	115%	130%
pH	2 to 5	5 to 7	3 to 5	3 to 5	3 to 7

SILICON PRODUCTS P. ASSOCIATES

285, PRINCESS STREET, JHAWAR HOUSE, 3RD FLOOR, MUMBAI-400002.INDIA

TEL NO. 022-22063006/22004033

E-mail- silicon535@gmail.com

FAX-(91-22)22033511

Website- www.siliconproducts.in